

**AP4-60**

Pellet Activated Carbon

Test	Specification		Calgon Carbon Test Method
	Min	Max	
CARBON TETRACHLORIDE, wt%	60	-	ASTM D3467
MOISTURE (AS PACKAGED), wt%	-	5	ASTM D2867
HARDNESS NUMBER	90	-	ASTM D3802
ASH, wt%	-	14	ASTM D2866
DENSITY (APPARENT), g/cc	T&R	-	ASTM D2854
IODINE NUMBER, mg/g	T&R	-	ASTM D4607
< 6 US MESH [3.35 mm] (PELLET), wt%	-	5	ASTM D2862

Typical Properties:

THIS PRODUCT IS NOT INCLUDED IN THE SCOPE OF CCC'S QUALITY SYSTEM CERTIFIED TO ISO 9001.
NOTE: CCC'S Quality System elements are applied whenever possible.

Calgon Carbon Corporation's activated carbon products are continuously being improved and changes may have taken place since this publication went to press. (2585-03/05/2012)