



SALES SPECIFICATION SHEET
DSR C 8X30
Granular Activated Carbon

Test	Specification		Calgon Carbon Test Method
	Min	Max	
IODINE NUMBER, mg/g	900	-	TM-4,ASTM D4607
MOISTURE (AS PACKAGED), wt%	-	2	TM-1,ASTM D2867
DENSITY (APPARENT), g/cc	-	0.60	TM-7,ASTM D2854
ABRASION	75	-	TM-9, AWWA B604
< 30 US MESH [0.600 mm] (PAN), wt%	-	5	TM-8,ASTM D2862

Typical Properties:

Methylene Blue, min 230

DSR C 8X30 is not to be used for Food Grade or Potable Water applications.

Calgon Carbon Corporation's activated carbon products are continuously being improved and changes may have taken place since this publication went to press. (12830-31/10/2013)



Geofluid Processors Private Limited

112, Building No.2, Mittal Industrial Estate,
Andheri Kurla Road, Marol, Andheri (E), Mumbai - 400 059.

+91-22- 6155 5888
info@geofluid.com

+91-22-6155 5800
www.geofluid.com